

# COBRA 40 POWER

PA 68% - EA 32%  
215 g/m<sup>2</sup> - 145 cm

## Valori di Solidità Colori / Colour Fastness Data Values

Colore / Colour	N°	Luce / Light ISO 105 B02		Sfregamento / Crocking Secco / Dry ISO 105 X12 Umidità / Wet		Lavaggio 40° - A1S / Washing 40° - A1S ISO 105 C06			Acqua Severa / Water Staining ISO 105 E01			Sudore Acido / Acid perspiration ISO 105 E04			Sudore Basico / Alkaline perspiration ISO 105 E04		
		C.C.	S.CO	S.CO	S.PL	S.PA	S.CO	S.PL	S.PA	S.CO	S.PL	S.PA	S.CO	S.PL	S.PA	S.CO	
APOCALYPTO	M299	3/4	4	4	4	3/4	4/5	4/5	4	4	4/5	4/5	4	4/5	4/5	4	4/5
DAYTONA R	X002	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
BIANCO	305	3/4															
HARLOCK	X369	5	4	3/4	4/5	3/4	4/5	4/5	4/5	4	4/5	4/5	4	4/5	4/5	4	4/5
BOMBAY	M158	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
PAT	M298	5	4/5	4	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
MOJITO	C054	2	4/5	4/5	4/5	4	3/4	4/5	4	4/5	4/5	4/5	4	4/5	4/5	3/4	4/5
NERO	X054	5	4	4	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4	4/5
FRIDA	S459	2	4/5	4	4/5	4	4	4/5	4	4	4/5	4	4	4/5	4	4	4
GAIA	X098	5	4/5	4	4/5	4	4/5	4/5	4/5	4	4/5	4/5	4	4/5	4	4/5	4/5
GOBI	M245	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
GRAVEL	M470	3/4	4/5	4/5	4/5	3/4	4	4/5	4	4/5	4/5	4	4/5	4/5	3/4	4/5	4/5
JOKER R	X012	2/3	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
PEWTER	M472	4	4	4	4	3	4	4	3/4	4	4	3/4	4	4	3/4	4	4
POSEIDON R	X012	5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
SAFFRON	C155	5	4/5	3/4	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4	4	4/5	4/5
SAND	C585	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4	4	4/5
SOUR	M310	2	4/5	4	4/5	4/5	4	4/5	4/5	4/5	4/5	4/5	4/5	4	4	4	4
TITANIO	S516	5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
VODKA	M263	3/4	4/5	4	4/5	3	3/4	4/5	3/4	4/5	4/5	3	4/5	4	2/3	4	4

Luce / Light	Valutazioni / Assessments	Altri Test / Other Tests	Valutazioni / Assessments
1	Debolissima / Very weak	1	Debole / Weak
2	Debole / Weak	2	Scarsa / Limited
3	Moderata / Moderate	3	Abbastanza buona / Fair
4	Abbastanza buona / Fair	4	Buona / Good
5	Buona / Good	5	Ottima / Excellent
6	Buonissima / Very good		
7	Ottima / Excellent	# Colori Fluorescenti / Fluor Colours	
8	Eccellente / Exceptional	C.C. = Cambio Colore / Colour discoloration S.CO = Stringimento su Cotone / Staining on Cotton S.PA = Stringimento su Poliammide / Staining on Polyamide	

Raccomandiamo la massima attenzione nella lettura dei valori di solidità. Sconsigliamo abbinamenti/intarsi tra colori che abbiano valori di solidità al lavaggio o acqua inferiori a 4/5. In caso di necessità di abbinamento/intarsio consigliamo sempre una prova preventiva.

Please pay special attention to the fastness values declared on the colour card. Combination of colours is not recommended when the fastness values of washing or water are lower than 4/5. In case of combination we suggest a trial before.

Agg. 08 - Date 02.04.2024

**M299**  
APOCALYPTO

**X054**  
NERO

**X012**  
POSEIDON

**X002**  
DAYTONA R

**S459**  
FRIDA

**C155**  
SAFFRON

**305**  
BIANCO

**X098**  
GAIA

**C585**  
SAND

**X369**  
HARLOCK

**M245**  
GOBI

**M310**  
SOUR

**M158**  
BOMBAY

**M470**  
GRAVEL

**S516**  
TITANIO

**M298**  
PAT

**X012**  
JOKER

**M263**  
VODKA

**C054**  
MOJITO

**M472**  
PEWTER